DIGITAL GLAZED VITRIFIED TILES

MADE IN INDIA

DIGITAL GLAZED VITRIFIED TILES

VITRIFIED TILES
DIGITAL GLAZED

CRISTIAN CERAMICHE
disegni italiani

MADE IN INDIA

DESIGN / BATCH NO

QUALITY

M.R.P (Inclusive of all taxes)

MFG. DATE

SAFETY FIRST

HANDLE WITH CARE

FRAGILE

STACKING

DIGITAL GLAZED VITRIFIED TILES

MADE IN INDIA

DIGITAL GLAZED VITRIFIED TILES

NORMAL Size : 60cm x 120cm / 600x1200mm

Quantity : 2 Pcs.

Coverage Area : 1.44 Sq.Mtr.

TILES LAYING INSTRUCTIONS

1. Tiles are laid under the assumption that the tiles will be laid with smooth finish and complete the plastering and curing at least two weeks prior to tiling.
2. Before fixing, tiles, lay them out in the desired pattern and make sure that they give an acceptable blend of shade, colour & Design . Also make sure that the tiles are acceptable to your satisfaction. Please not that certain amount of shade and size variation is inherent in the manufacturing of fully vitrified normal tiles. THE COMPANY WILL NEAR INCOMPLETE AFTER THE TILES ARE FIXED.
3. For fixing these tiles, we recommend the use of tile fixing adhesive. For fixing these tiles, follow the tiles fixing instructions provided along with adhesives.
4. For Fixing TILES on Walls, we recommend the use of tile fixing adhesive. Please follow the manufacturer's instructions for the same.
   a) Use cement and sand mortar in the ratio of 1:6 Add some water to created a consistent paste.
   b) Once the mixing has been completed do not add any further water and use the same within one hour.
   c) Apply a thin layer of the mixture to the back of the tile and a slightly thicker layer to the surface of the area. Apply a fine slurry to the black of the tile.
   d) ensure proper and full loading. Press gently for even adherence at the back of the tile. DO NOT USE AN IRON HAMMER OR SOME HEAVY MATERIAL TO PRESS THE TILE.
5. For Fixing TILES on Dado, we recommend the use tiles fixing adhesive. Please follow the manufacturer's instructions for the same. we do not recommend the use of sand and cement for fixing on Dado.
6. Mode and lay out the tiles from the center of the area to laid so that cut tiles, if any will be on the outer edges towards the walls.
7. Tiles should be laid with 2 to 3 mm spacing between each tile to allow for possible expansion as per BIS/ITA tolerance norms. This would give the coverage area as mentioned in the carton.
8. Complete the laying process a day of in lay the center of the tiles firstly then the place along the walls/floors.
9. Allow 3-4 days for bed curing. After this period fill the joints with grouts.
10. Fifteen minutes after finishing the grouting process, wipe off excess grout with a damp sponge and polish the tiles with a soft and dry cloth for a clean surface. The tiles can also be cleaned with a mild acid (However, Hydrofluoric acid and its derivatives should not be used.)
11. Tiles are laid under the assumption that the tiles will be laid in one of the area. In case of problems arising out of non-adherence to these fixing instructions.
12. No complaints will be entertained after laying of the tiles.

NOTHING IN THESE INSTRUCTIONS IS A SUBSTITUTE FOR GOOD WORKMANSHIP & SUPERVISION

KINDLY LOOK FOR THE ARROW (➡) ON THE BACK OF THE TILE AND FOLLOW THE LAYING PATTERN AS SHOWN ABOVE

OR

4.2mm Spacer (Grout)

WE ADVISE YOU TO MAINTAIN MIN. 2MM GROUTING SPACE BETWEEN TWO TILES AND PROVIDE THE EXPANSION JOINTS WHEREVER REQUIRED.

DIGITAL GLAZED VITRIFIED TILES